


# Jiangsu Oliter Energy Technology Co.,Ltd


Jiangsu Oliter Energy Technology Co.,Ltd was founded in 1998,covered 42,000M2,annual throughput reaches 750000KVAH.Over the years ,Oliter is focusing on the integration of R&D,production,Marketing and application of VRLA,Gel battery,Lithium battery.By the support of South China Normal University,Xi'An JiaoTong University and Other scientific research institutes,Oliter has built up the post-doctoral workstations.Till now,Oliter has achieved 7 series,more than 100 models of batteries.Oliter has became the largest production base of solar energy storage battery in northern Jiangsu.

### JGFM500-2 GEL BATTERY









#### Features

"Oliter" battery ,Maintenance free and easy to use, Contemporary advanced technology research and development of new high-performance batteries, It can be widely used in solar energy, wind energy, telecommunication systems, off-grid systems , UPS and other fields. The designed life for the battery could be eight years up for float use

### Technology data

Reted Voltage	Capacity (10hr,1.8 0V/Cell)	Weight	Max Discharge Current	Max Charge Current	Self- Discharge (25℃)	Using Temperature	Cover Material
2V	500Ah	29.6Kg	30I10A (3min)	≤0.25C10	≤3%/month	15℃~25℃	ABS

Using Temperature	Charge Voltage (25℃)	Temperature Compensation Coefficient(25°C)	Cycle life	Capacity Affected by Temperature
Discharge:-45°C~50°C Charge: -20°C~45°C Storage: -30°C~40°C	Float Charge: 2.23V-2.28V Average Charge: 2.35-2.40V	Float Temperature Compensation Coefficient -3mV/Cell°C  Equalization Temperature Compensation Coefficient - 4mV/Cell°C	100%DOD 1260times 80%DOD 1770times	105 % @ 40℃ 90 % @ ೮℃ 70 % @ -20℃

#### Certificate


ISO9001 ISO14001 CE CGC TLC

High and New Technology Products Certification

Standards:

GB/T 19638.2-2005 YD/T799-2002 JISC8704-2:1999

#### Cycle use curve(Amps,20)

































## Jiangsu Oliter Energy Technology Co.,Ltd


#### Performance characteristics














**Note** The above data are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice.























